



PRODUCT INFORMATION



1. Product specification

Product Number	Product Description	Surface	Material	Classification
NTD35	Nitrile Powder Free Disposable Gloves 3.5 g +/- 0.2	No Textured	Synthetic Nitrile	Industry

Width and Length	Size	Total Length (mm.)	Width (mm.)	Weight (gm.)
Reference Standard ASTM D6319 (S2/AQL 4.0)	Small	Min 220	80 ± 10 mm	3.1 ± 0.2
	Medium	Min 230	95 ± 10 mm	3.5 ± 0.2
	Large	Min 230	110 ± 10 mm	3.9 ± 0.2
	X-Large	Min 230	120 ± 10 mm	4.3 ± 0.2

Thickness (single Wall)	Location of Thickness Measurement	Single Wall Thickness (mm)
Reference Standard ASTM D6319 (S2/AQL 4.0)	Finger (13 mm from the tip)	0.07 +/- 0.01 mm
	Palm (center of the palm)	0.07 +/- 0.01 mm
	Cuff (25 mm from the bead)	0.07 +/- 0.01 mm

Physical Properties	Characteristics	Before Ageing	After Ageing 7 day @ 70°C ± 2 hours
EN455 part 2 (S2/AQL 4.0)	Force at break (N)	Min 7	Min 6
ASTM D6319 (S2/AQL 4.0)	Tensile Strength (MPa)	Min 14	Min 14
	Elongation at Break (%)	Min 500	Min 400

Characteristics	Inspection Level & Sampling Plan	AQL & Acceptance Limit
Pinhole (water tight test)	G-1	AQL 2.5
Major Defects	G-1	AQL 2.5
Physical Properties Related Non-Conformities	S-2	AQL 4.0
Physical Dimension	13 Pcs	AQL 4.0
Surface Residual Extractable (Powder)	As per ASTM D6124 Test Method	Max 2mg/dm ²
Water Extractable Protein	As per ASTM D5712 Test Method	Below 50mg/dm ²

2. Sectors of Use:

- Automotive industry and the automotive parts
- Gem and jewelry industry
- Electronics industry